

1.7147

20MnCr5 / 20HG

STAL DO NAWĘGLANIA

APPLICATION

Parts with predominant high-wear stress which works under heavy load , piston pins, levers, worm wheels, bushings, camshafts and other vehicle parts.

CHEMICAL COMPOSITION

Chemical composition (in weight %)

Element	C	Si	Mn	P	S	Cr	Mo	Ni	Cu
min	0.17	maks.	1.10	max.	max.	1.50	0.25	1.40	max.
max.	0.22	0.04	0.90	0.025	0.035	1.80	0.35	1.70	0.40

TREATMENT

Jominy test	900 °C (± 5 °C) at least 30 min. austenitizing time (reference value)
Carburizing	880 - 980 °C
Direct and single hardening	820 - 860 °C
Core hardening	860 - 900 °C
Case hardening	780 - 820 °C
Tempering	150 - 200 °C mind. 60 min. (approx.)

ADDITIONAL HEAT TREATMENT

Normalising	840 - 870 °C
Soft annealing	650 - 700 °C
Intermediate annealing	650 - 700 °C

MECHANICAL PROPERTIES

Modulus of elasticity [GPa]	215
Shear modulus [GPa]	83
Poisson ratio	0.30